## The Delphion Integrated View

Tools: Add to Work File: Create new Work File Get Now: PDF | More choices... Go to: Derwent... View: INPADOC | Jump to: Top

> JP62005842A2: MANUFACTURE OF FIBER REINFORCED RESIN MOLDED **₽**Title:

**PRODUCT** 

JP Japan **P**Country:

KONDO KATSUMI; **V**Inventor:

**HORI RYUZO:** 

TSUCHIYA YASUHIRO: **MIYAZAKI SHOJI**;

TOYOTA MOTOR CORP **P**Assignee:

News, Profiles, Stocks and More about this company

1987-01-12 / 1985-07-01 Published / Filed:

**P**Application

JP1985000144309

Number:

B29D 23/22; B29C 67/14; **₽IPC Code:**

1985-07-01 JP1985000144309 Priority Number:

**PAbstract:** 

PURPOSE: To provide the molding process capable of further complicating the shape of a large molded product by a method in which after a continuous fiber bundle impregnated with resin has been wound like the meshes of a net arround a mandrel, the inner pressure of the mandrel is heightened, while constraining said bundle with a heated mold, whereby the impregnating resin is

CONSTITUTION: The bundles 2 of glass fibers are passed from bobbins 1 through an epoxy resin bath 3 and impregnated with resin, and it is wound on the hollow mandrel 4 made of easily deformable silicon rubber. Said material is constrained, applying a load W, with the mold 7 composed of a top force 7a and a bottom force 7b, and including a heating device therein. Then, the pressure in between the mold 7 and the hollow mandrel is heightened to 5W7kg/cm2, applying gas pressure F from a pipe 5. If the temperature of the mold 7 is raised to 100W150°C, the fiber bundle 6 impregnated with resin is cured after 1W4hr. Then, the mold 7 is removed and the gas in the hollow mandrel 4 is sucked and exhausted.

COPYRIGHT: (C)1987, JPO& Japio

**Family:** None


DERABS C87-047360 DERC87-047360 **POther Abstract** 

Info:









**Image** 

1 page



this for the Gallery...

© 1997-2003 Thomson Delphion

Research Subscriptions | Privacy Policy | Terms & Conditions | Site Map | Contact Us | Help